TECHNICAL DATA SHEET CT PowderRange 625 E



Introduction

PowderRange metal Additive Manufacturing powders from Carpenter Additive are developed with the needs of the busy AM facility in mind.

- Easy ordering
- Standard specifications
- 24-hour shipment
- Sold in easy-to-handle multiples of 10 kgs
- Easy repeat orders to optimize inventory management

This leaves you free to concentrate on the design and build of your AM parts, confident that PowderRange metal AM powders from Carpenter Additive will add reliability and consistency to your AM built parts.

Characteristics

PowderRange 625 E Nickel Chromium Alloy is a Ni-Cr superalloy with significant mass fractions of molybdenum and niobium. The addition of molybdenum and niobium gives the alloy high strength and toughness in the annealed condition. Although it can be precipitation strengthened, it is considered a solid solution strengthened superalloy. As a consequence, it has superior properties in the 'as processed' state with Laser Powder Bed Fusion relative to PowderRange 718 that requires additional heat-treating steps to achieve maximum mechanical properties.

Applications

PowderRange 625 has a wide range of applications within aerospace, automotive and the marine industry, and its particularly suitable for applications where corrosion and oxidation resistance at high temperatures is required.



For worldwide contact details please visit www.carpenteradditive.com

Whilst every reasonable effort has been made to verify that the information contained in this data sheet is correct, there are no guarantees or warranties (express or implied) concerning the accuracy or completeness of the information provided and expressly excludes all liabilities for any inaccuracies in this document or failure to achieve the stated levels. Carpenter Additive is a business unit of Carpenter Technology Corporation.

TECHNICAL DATA SHEET CT PowderRange 625 E



Chemical composition

| Element | | Minimum wt% | Maximum wt% |
|---------|--------------------|-------------|-------------|
| Al | Aluminum | | 0.40 |
| С | Carbon | | 0.10 |
| Со | Cobalt | | 1.0 |
| Cr | Chromium | 20.0 | 23.0 |
| Cu | Copper | | 0.50 |
| Fe | Iron | | 5.0 |
| Mn | Manganese | | 0.50 |
| Мо | Molybdenum | 8.0 | 10.0 |
| Ν | Nitrogen | | 0.02 |
| Nb+Ta | Niobium + Tantalum | 3.15 | 4.15 |
| Ni | Nickel | Balance | |
| 0 | Oxygen | | 0.03 |
| Р | Phosphorus | | 0.015 |
| S | Sulfur | | 0.015 |
| Si | Silicon | | 0.50 |
| Ti | Titanium | | 0.40 |

Particle size distribution – CT PowderRange 625 E

| Size | Value | Method |
|---------|-------------|----------------|
| -45 µm | 10 Volume % | Sieve Analysis |
| +106 µm | 10 Weight % | Sieve Analysis |



For worldwide contact details please visit www.carpenteradditive.com

Whilst every reasonable effort has been made to verify that the information contained in this data sheet is correct, there are no guarantees or warranties (express or implied) concerning the accuracy or completeness of the information provided and expressly excludes all liabilities for any inaccuracies in this document or failure to achieve the stated levels. Carpenter Additive is a business unit of Carpenter Technology Corporation.



Mechanical properties (indicative only)

| Property | | As built |
|--------------------------------------|------------------------------|-------------------------------|
| Tensile Strength [1] | Horizontal Direction (XY) | 950 - 1050 MPa 138-152 ksi |
| Tonolo Chongan [1] | Vertical Direction (Z) | 875 - 950 MPa 127-138 ksi |
| Yield Strength [1] | Horizontal Direction (XY) | 700 - 750 MPa 102-109 ksi |
| | Vertical Direction (Z) | 575 - 625 MPa 83-91 ksi |
| Veure's Madulus [1] | Horizontal Direction (XY) | 165 - 185 GPa 24-27 msi |
| Young's Modulus [1] | Vertical Direction (Z) | 135 - 155 GPa 20-22 msi |
| Elongation [1] | Horizontal Direction (XY) | 30 - 35 % |
| | Vertical Direction (Z) | 35 - 45 % |
| Hardness [2] | 300 - 330 HV0.5 | |
| Coefficient of Thermal Expansion [3] | 12.8 × 10 ⁻⁶ m/mK | |
| Thermal Conductivity [3] | 9 - 10.5 W/mK | |

1. As built. Mechanical testing in accordance with ISO 6892

2. As built. Hardness test in accordance with ASTM E384-11

3. In the range of 20°C (68°F) to 100°C (212°F)

Range of mechanical properties encompasses expected values across multiple machine platforms



For worldwide contact details please visit www.carpenteradditive.com

Whilst every reasonable effort has been made to verify that the information contained in this data sheet is correct, there are no guarantees or warranties (express or implied) concerning the accuracy or completeness of the information provided and expressly excludes all liabilities for any inaccuracies in this document or failure to achieve the stated levels. Carpenter Additive is a business unit of Carpenter Technology Corporation.

TECHNICAL DATA SHEET CT PowderRange 625 E



Similar materials

| Company | Alternative Title |
|---------------------|---------------------------|
| LPW | 625 Nickel Chromium Alloy |
| UNS | N06625 |
| Other Generic Names | Inconel 625 |
| 3D Systems | N/A |
| Concept Laser | CL 101NB |
| EOS | IN625 |
| Realizer | N/A |
| Renishaw | In625-0402 |
| SLM Solutions | Inconel 625 |
| TRUMPF | N/A |

Ordering information

CT PowderRange 625 is available from stock and dispatched within 24 hours of receipt of order. Our PowderRange metal AM powders are sold in multiples of 10 kgs giving you the flexibility to order just the volume you need to maintain efficient material stock levels.

All our PowderRange materials are supplied with a full metal powder certification to Carpenter Additive's standard material specification, reporting size distribution, flow, chemistry and morphology.

| Code | Description | Unit volumes |
|----------------------|--|--------------|
| CT PowderRange 625 E | Electron Beam powder bed fusion machines | 10 kgs |

Further information

To make an enquiry, please contact <u>powderrange@carpenteradditive.com</u>. Alternatively, for EU/Row, call +44 (0)1928 240 530 and for USA call +1-412-788-2856. You can visit us at <u>www.carpenteradditive.com</u>.



For worldwide contact details please visit www.carpenteradditive.com

Whilst every reasonable effort has been made to verify that the information contained in this data sheet is correct, there are no guarantees or warranties (express or implied) concerning the accuracy or completeness of the information provided and expressly excludes all liabilities for any inaccuracies in this document or failure to achieve the stated levels. Carpenter Additive is a business unit of Carpenter Technology Corporation.